

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 55-010412

(43)Date of publication of application : 24.01.1980

(51)Int.Cl.

C03B 37/00
G02B 5/172

(21)Application number : 53-081430

(71)Applicant : NIPPON TELEGR & TELEPH CORP <NTT>

(22)Date of filing : 06.07.1978


(72)Inventor : KAWACHI MASAO
SUDO SHOICHI
SHIBATA NORIYOSHI
EDAHIRO TAKAO

(54) PRODUCTION OF ANHYDROUS GLASS BASE MATERIAL FOR OPTICAL FIBER

(57)Abstract:

PURPOSE: To obtain the title material with reduced OH group content and free from transition metals, etc. by exposing a porous glass sintered body to high purity Cl₂ obtd. by thermally decomposing vapor of a liquid Cl-contg. cpd. and removing solid matter when the body is converted into transparent glass.

CONSTITUTION: SiO₂-based glass-forming substance is attached to one end of support rod 2 with core glass-forming burner 4 and clad glass-forming burner 5, and cylindrical porous glass sintered body 7 is grown while moving rod 2 with rotary pulling device 3. Next body 7 is converted into transparent glass with heater 9. At this time, He is blown into liquid Cl-contg. cpd. 10 such as S₂Cl₂ or SiCl₄, and vapor formed is introduced into quartz tube 15 in thermal decomposition furnace 14. Solid matter-contg. Cl₂ formed is passed through filter 17 to remove the solid matter, and high purity Cl is introduced into container 1 through duct 18 and contacted to body 7.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]